

Material Specification Sheets

Colorjet

Parameter	Unit	Full- Colored Plaster
Build Space	mm	350x250x200
Tensile strength	MPa	14,2
Elongation at break	%	0,23
Modulus of elasticity	MPa	9450
Flexural Strength	MPa	31,1
Flexural Modulus	MPa	7163
HDT, °C @ 0.45MPa	°C	k.A.
HDT, °C @ 1.82MPa	°C	k.A.
Izod Notched Impact	J/m	k.A.
Water Absorption	%	k.A.
Tg (Glass Transition Temperature)	°C	k.A.
Shore Hardness (D)	Scale D	k.A.
Shore Hardness (A)	Scale A	k.A.
Rockwell Hardness	Scale M	k.A.
Polymerized density	g/cm ³	k.A.
Ash content	%	k.A.

